



Tannin-Bonded *Rhizophora* spp. Particleboards as Water Equivalent Phantom Material for High Energy Photons and Electrons

M. F. Mohd Yusof^{1,3*}, P. N. K Abd Hamid¹, R. Hashim², A. A. Tajuddin¹, S. Bauk¹, and N. Mohd Isa¹

¹School of Physics, Universiti Sains Malaysia, 11800 Penang, Malaysia

²School of Industrial Technology, Universiti Sains Malaysia, 11800 Penang, Malaysia

³School of Health Sciences, Universiti Sains Malaysia, 16150 Kelantan, Malaysia

⁴Medical Physics Group, Malaysian Nuclear Agency, 43000 Selangor, Malaysia

PAPER INFO

Paper history:

Received 09 December 2017

Accepted in revised form 30 December 2017

Keywords:

Rhizophora spp.

Phantom material

Mass attenuation coefficient

Percentage depth dose

ABSTRACT

Phantom materials are important tools for quality control and dosimetry works in medical physics. The tannin-bonded *Rhizophora* spp. particleboards in were fabricated as phantom and the dosimetric properties at high energy photons and electrons were evaluated. The particleboards were fabricated at dimensions of 30 x 30 x 1 cm³ and target density of 1.0 g/cm³ based on the commonly used solid water phantoms in radiotherapy. The effective atomic number of the particleboard was determined based on the elemental compositions measured using energy dispersive x-ray analysis (EDXA). The mass attenuation coefficients at high energy photon were measured at 16.59-25.26 keV photons and ⁶⁰Co and ¹³⁷Cs gamma energies. The percentage depth dose and beam parameters of the particleboards were measured at 6 MV photons and 6 MeV electrons using Gafchromic EBT2 film and treatment planning system (TPS) software. The results showed that the effective atomic number and electron density of the particleboards were close to the value of water. The mass attenuation coefficient at high energy photons were close to the XCOM value of water. The percentage depth dose at high energy photons and electrons showed an agreement to the value in water and solid water phantom within 10% at all measured depths. The overall results indicated the suitability of tannin-bonded *Rhizophora* spp. as phantom material for high energy photons and electrons.

doi: 10.5829/ijee.2017.08.04.05

INTRODUCTION

Phantoms are the materials that simulate the absorption and scattering characteristics of human soft tissues towards ionizing radiations [1]. Phantoms become important tools for quality assurance, calibration and dosimetric studies involving high energy photons and electrons to ensure the precision of beam delivery in a radiotherapy treatment. An ideal phantom material shall have density and attenuation properties similar to the human soft tissues. The commonly available dosimetric protocols had suggested water as phantom material for high energy photons and electrons due to its near density to human soft tissue. The use of water however is not always convenience due to its liquidity and compatibility of most radiation dosimeters to be used in water. Several solid-state phantoms such as acrylic, Perspex® and polystyrene were developed to substitute

water but still failed to accurately simulate the attenuation of water at various range of photons.

Rhizophora spp. had been identified as potential phantom material due to its mass density and attenuation properties near to the value of water [2,3]. A dosimetric study on high energy photons and electrons also showed good agreement of depth dose in raw *Rhizophora* spp. wood to water [4]. The use of raw *Rhizophora* spp. wood however came into several limitations including limited size for full standard phantom size, and tendency to crack and bend over period of time. Shakheer et al., [5] had studied the fabrication of *Rhizophora* spp. particleboards that enables the fabrication at various size and shapes. The results showed that the fabrication of *Rhizophora* spp. particleboards did not significantly change its attenuation properties towards photons. The fabrication of *Rhizophora* spp. particleboards however had reduced the physical strength of *Rhizophora* spp. phantoms [6,5]. The use of synthetic-based adhesives such as urea-formaldehyde (UF) commonly used in industry had

* Corresponding author: M.F. Mohd Yusof
E-mail: mfahmi@usm.my

significantly lowered the density and mass attenuation coefficients of *Rhizophora* spp. [7,8]. The biological-based adhesives on the other hand were found to increase the physical properties of *Rhizophora* spp. particleboards and at the same time retaining its attenuation properties at various clinical applications [9,10,11].

Tannin had been widely used as adhesives for particleboard and wood panel industries [12,13]. Previous study had indicated the potential use of *Rhizophora* spp. tannin extracted from the bark as potential adhesive material for *Rhizophora* spp. phantom material at mammographic X-ray energy ranges [14]. The present study focused on the use of commercialized tannin in form of tannic acid powder as bio-adhesive material for *Rhizophora* spp. particleboards in application of high energy photons and electrons.

The commercialized tannin used in the present study having the molecular formula of C₇₆H₅₂O₅₆ which is comparable to the composition of soft tissues with a molecular weight of 1701.2 g/mol. A calculation of effective atomic number showed that tannic acid has an effective electron density of 6.937, which is near to the value of water (7.42) [15].

MATERIAL AND METHODS

Fabrication of Particleboard Phantoms

A set of thirty *Rhizophora* spp. particleboards were fabricated at target density of 1.0 g/cm³ and dimensions of 30 cm x 30 cm x 1 cm according to the commonly used solid water phantoms. An amount of 10% tannin were added during the fabrication of the particleboards based on the measured dried mass of *Rhizophora* spp. wood particles required to achieve the target density. The moisture content of the wood particle was kept lower than 7% to prevent water accumulation during the hot pressing that would cause blistering and swelling to the particleboard surface. The particleboards were fabricated by the method of hot pressing with temperature and pressure of 200°C and 20 MPa respectively based on the study by Marashdeh et al., [6]. The average density of the particleboards were measured using gravimetric method based on the external dimensions given by the equation

$$\rho = \frac{\text{length} \times \text{width} \times \text{thickness}}{\text{mass}} \quad (1)$$

Elemental Compositions and Effective Atomic Number

The percentage of elemental compositions of the tannin-bonded *Rhizophora* spp. particleboards was measured using energy dispersive X-ray analysis (EDXA). The effective atomic number Z_{eff} of the particleboard was

calculated based on the study by Duvauchelle et al., [16] using the equation

$$Z_{\text{eff}} = \left[\sum_{i=1}^n (\alpha_i z_i^m) \right]^{\left(\frac{1}{m}\right)} \quad (2)$$

with α_i and z_i are the electron fraction and the atomic number of the i^{th} element in the sample, and m is the experimental coefficient for biological materials and water, having a value of 3.4. The electron fraction of the i^{th} element was calculated using the equation

$$\alpha_i = \frac{w_i \left(\frac{z_i}{A_i} \right)}{\sum w_i \left(\frac{z_i}{A_i} \right)} \quad (3)$$

with w_i and A_i are the fractional weight and atomic mass of the i^{th} element respectively. The calculated value of Z_{eff} of the *Rhizophora* spp. particleboards were compared to the value of water [15].

Determination of CT Number

The CT number of a medium is proportional by the its attenuation property as shown by the equation

$$\text{CT number} = 1000 \frac{\mu - \mu_w}{\mu_w} \quad (4)$$

With μ and μ_w is the linear attenuation coefficient of the medium and water respectively. The CT number of tannin-bonded *Rhizophora* spp. was measured to determine its water and tissue equivalent property. The particleboard was sawn circularly with diameter of 3 cm made compatible for electron density phantom model CIRS 062M. The CT image of the particleboards was obtained at 120 kVp CT X-ray energy with 250 mAs exposure factors using abdominal scanning protocol. The CT number of the particleboard was measured from the CT image and compared to the value of water and other soft tissues including adipose, liver, muscle and breast density plug phantoms of the electron density phantom. The density profile was plotted to determine the uniformity of density in the tannin-bonded *Rhizophora* spp.

Measurement od Mass Attenuation Coefficients

The mass attenuation coefficients of tannin-bonded *Rhizophora* spp. particleboards at low energy photons were measured using an XRF configuration as shown in Figure 1 (a). An annular ²⁴¹Am source with peak gamma energy of 59.59 keV was used in the XRF configuration in conjunction with niobium, molybdenum, palladium and tin plates that provided $\text{k}\alpha_1$ photons of 16.59, 17.46, 21.21 and 25.26 keV respectively. The transmitted photons were collected by a low energy germanium detector (LEGe) connected to a single channel analyzer (SCA). The mass attenuation coefficients at high energy photons were measured using Ludlum configuration in

conjunction with ^{137}Cs and ^{60}Co sealed sources that provided gamma energies of 0.662 and 1.2 MeV respectively. The transmitted photons in XRF and Ludlum configurations were measured as count per minute (CPM). The linear attenuation coefficients of the particleboards were determined based on the transmitted photons according to the Beer-Lambert law given by the equation

$$I = I_0 e^{-\mu x} \quad (5)$$

with I_0 is the initial intensity of photons, μ is the linear attenuation coefficient of the sample, and x is the thickness of the particleboard samples. The value of the linear attenuation coefficient was calculated using the equation

$$\mu = \frac{1}{x} \ln \left(\frac{I_0}{I} \right) \quad (6)$$

The value of the mass attenuation coefficient is obtained by dividing the value of the linear attenuation coefficient by the density of the particleboard.




Figure 1. The experimental set up of (a) X-ray fluorescence (XRF) and (b) Ludlum configuration used for determination of mass attenuation coefficients

Measurement of Percentage Depth Dose at High Energy Photons and Electrons

The percentage depth doses (PDD) of tannin-bonded *Rhizophora* spp. particleboards were measured using a clinical linear accelerator. The depth dose in the particleboards were measured at 6 MV photons and 6 MeV electrons using Gafchromic EBT2 radiochromic film dosimeter (EBT2) and treatment planning system (TPS) computer. The depth dose using EBT2 film was measured by placing the film at the midplane of the particleboards. Irradiations were made parallel to the

beam with 10 x 10 cm field size and 100 cGy dose based on IAEA TRS398:2000 codes of practice as shown in Figure 2(a). The depth dose using TPS were done by scanning the particleboards using a CT scan as an input to the TPS system. The beams were simulated according to IAEA TRS398:2000 (10 x 10 cm field size and 100 cGy dose) as shown in Figure 2(b). The PDD values of the particleboards were based on the ratio between the dose at depth, D to the maximum dose, D_{max} given by the equation

$$PDD = \frac{D}{D_{max}} \times 100\% \quad (7)$$

The PDD curve of the particleboards were plotted and compared to water and solid water phantoms as standard phantom materials used in radiotherapy.




Figure 2. The measurements of PDD using (a) EBT2 film dosimeter and (b) treatment planning system (TPS)

RESULTS AND DISCUSSION

Analysis of Physical Properties

The average density of tannin-based *Rhizophora* spp. particleboard phantoms measured using gravimetric method is presented in Table 1. The results showed that all particleboards had achieved density near to the value of water (1.0 g/cm^3). The results were in good agreement to the previous study by Bradley et al., [2] who measured the average density of raw *Rhizophora* spp. wood. The densities of the particleboards also

showed good uniformity shown by the standard deviation value.

The percentage of elemental compositions of tannin-based *Rhizophora* spp. particleboards is presented in Table 2. The results showed that the elemental compositions of tannin-bonded *Rhizophora* spp. showed high percentage of carbon and oxygen which is similar to the elemental compositions of human soft tissue. The calculation of Z_{eff} also showed close value to that in water indicating its water equivalent property. The results were in good agreement to the previous studies by Bradley et al.,[2] who measured the Z_{eff} of raw *Rhizophora* spp. wood. The results were also in good agreement to the previous studies on the fabrication of particleboards as phantoms [9,10,14,11,15].

TABLE 2. The percentage of elemental compositions and effective atomic number of *Rhizophora* spp. particleboards

Sample	Elemental composition (%)					Z_{eff}
	Hydrogen	Carbon	Oxygen	Nitrogen	Fluorin	
Tannin-bonded <i>Rhizophora</i> spp. ^a	-	51.25	43.11	-	5.64	7.22
Binderless <i>Rhizophora</i> spp. ^b	5.41	48.32	54.4	0.03	-	-
<i>Rhizophora</i> spp. raw wood ^c	3.78	40.16	47.9	3.78	-	-
Water ^d	11.11	-	88.89	-	-	7.42
Tannin ^a	2.79	49.03	48.18	-	-	6.95

^aCurrent study, ^bMarashdeh et al (2012), ^cBradley et al (1991), ^dAAPM-21 (1983)

TABLE 3. The average CT numbers of tannin-bonded *Rhizophora* spp. Particleboards and other tissue equivalent phantoms

Density plug phantom	Density (g/cm ³)	Mean CT Number (HU)			Standard Deviation
		Average	Max	Min	
Adipose Tissue	0.970	-78.75	60	-207	32.54
Breast (50/50)	0.990	-52.09	76	-164	38.05
Water	1.004	-11.60	119	-133	37.19
Muscle	1.060	27.36	164	-93	29.69
Tannin-bonded <i>Rhizophora</i> spp.	1.001	-18.43	94.53	-118.47	39.78

Analysis of Mass Attenuation Coefficients

The mass attenuation coefficients of tannin-bonded *Rhizophora* spp. particleboards at low and high energy photons are presented in Table 4. The mass attenuation coefficients of the particleboards were found to be

The average CT number of tannin-bonded *Rhizophora* spp. particleboards at 120 kVp CT X-ray energy is presented in Table 3. A comparison of CT number to the other tissue equivalent density plug phantoms showed close value of CT number to water. The results had indicated the water equivalent property of tannin-bonded *Rhizophora* spp. particleboards based on the CT number [17].

TABLE 1. The average density of tannin-bonded *Rhizophora* spp. particleboards.

Density, ρ (g/cm ³)		Standard Deviation
Max	Min	Average
1.021	0.985	1.001
		0.014

close to the calculated value of water using XCOM [18]. A comparison to the raw *Rhizophora* spp. wood showed that the fabrication of particleboards had improved the attenuation properties of *Rhizophora* spp.

TABLE 4. The linear and mass attenuation coefficients of tannin-bonded *Rhizophora* spp. particleboards at low and high energy photons

Energy	Tannin-bonded <i>Rhizophora</i> spp.	Raw <i>Rhizophora</i> spp. wood	Water (XCOM)
Nb (16.59 keV)	μ μ/ρ	1.142 1.072	1.136 1.135
Mo (17.46 keV)	μ μ/ρ	1.072 1.011	0.921 0.921
Pd (21.21 keV)	μ μ/ρ	0.731 0.718	0.659 0.659
Sn (25.26 keV)	μ μ/ρ	0.486 0.478	0.440 0.440
¹³⁷ Cs (0.662 MeV)	μ μ/ρ	0.079 0.079	0.067 0.067
⁶⁰ Co (1.2 MeV)	μ μ/ρ	0.056 0.054	0.053 0.054

The mass attenuation coefficients of a material are an important parameter to determine the attenuation properties and the suitability of a material as phantoms. A phantom material shall have similar value of mass attenuation coefficients to the standard phantom material (water and soft tissues). The mass attenuation coefficients of tannin-bonded *Rhizophora* spp. particleboards were found to be close to the values of water calculated using XCOM at low and high energy photons. The results was in good agreement to the previous studies on the attenuation properties of fabricated *Rhizophora* spp. particleboards as phantoms [9,10,6,19,14,11]. The results had also indicated the suitability of the experimental set up XRF and Ludlum configurations as methods for the measurements of mass attenuation coefficients.

Analysis of Percentage Depth Dose in High Energy Photons and Electrons

The PDD of tannin-bonded *Rhizophora* spp. particleboards at 6 MV photons and 6 MeV electrons using EBT2 film dosimeter and TPS computer is shown in Figure 3 and 4 respectively. The PDD of tannin-bonded *Rhizophora* spp. were in good agreement to solid water and water phantoms at 6 MV photons and 6 MeV electrons within maximum percentage of discrepancies of 10% as shown in Figure 3(a) and 3(b) respectively when measured using EBT2 film dosimeter. The PDD measurement using TPS computer showed that the PDD of tannin-bonded *Rhizophora* spp. were in good agreement to solid water phantoms within 6% at 6 MV photons and 6 MeV electrons as shown in Figure 4(a) and 4(b) respectively. A comparison to water (ionization chamber) however showed significant different of PDD at depth beyond d_{max} for 6 MeV electrons.

The PDD had been commonly used to determine the attenuation and dosimetric properties of a medium in clinical photons and electrons. The dose at depth as well as the maximum dose received resulted from the delivery of photons and electrons shall be evaluated from the PDD curve. The PDD also had become the basis for the output calibration and quality assurance for high energy photons and electrons. Film dosimeters including the EBT2 on the other hands had been extensively used for dosimetry works in radiotherapy due to its good spatial resolution and wide range of dose range especially in a mixed-field radiation beam such as the intensity modulated radiation therapy (IMRT) [20,21]. The TPS software had been commonly used in treatment planning in radiotherapy that includes the clinical set up of the radiation beams and the simulations of dose based on the CT images and planned radiation beams. The PDD of tannin-bonded *Rhizophora* spp. were found to be in good agreement to water and solid water commonly used as standard phantoms in radiotherapy in both 6 MV photons and 6 MeV electrons. A comparison between the PDD curves in EBT2 film and TPS showed good agreement between the two methods. The surface doses of the particleboards were found to be lower than that in water and solid water. The PDD of the particleboards showed an excellent agreement within 4% to water and solid water at the build-up regions in both photons and electrons. The percentage of discrepancies however increased at depths beyond the d_{max} within 10% to water and solid water. The overall results were in good agreement to the previous work on the PDD of raw *Rhizophora* spp. wood in 6 MV photons and 5 MeV electrons [4].




Figure 3. The PDD curve of (a) 6 MV photons and (b) 6 MeV electrons measured using EBT2 film.




Figure 4. The PDD curve of (a) 6 MV photons and (b) 6 MeV electrons measured using treatment planning system (TPS).

CONCLUSION

The fabricated tannin-bonded *Rhizophora* spp. particleboards had achieved the effective atomic number and CT number close to the value of water indicating its water equivalent properties to be used as phantoms. The measurement of mass attenuation coefficients also showed that the value of tannin-bonded *Rhizophora* spp. were in good agreement to the calculated value of water using XCOM. The measurements of percentage depth dose at high energy photons and electrons had shown good agreement to water and solid water that are commonly used as phantoms in radiotherapy. A comparison of percentage depth dose curve also showed a good consistency between the EBT2 film and TPS software. The overall results had indicated the suitability of tannin-bonded *Rhizophora* spp. particleboards to be used as phantoms for dosimetry works involving high energy photons and electrons.

ACKNOWLEDGEMENT

The authors would like to acknowledge the financial support by Research Universiti Grant no. PSPTEKIND1000000004178 by Universiti Sains Malaysia. The authors also acknowledge the Oncology, Radiotherapy and Nuclear Medicine Department, Hospital Universiti Sains Malaysia for the use of linear accelerator and TPS computer.

REFERENCES

- Khan, M. F., 2010. The physics of radiation therapy, Lippincott William & Wilkins, Philadelphia
- Bradley, D. A., Tajuddin, A. A., Che Wan Sudin, C. W. A., and Bauk, S. 1991., Photon attenuation studies on tropical hardwoods. International Journal of Radiation Applications and Instrumentation. Part A. Appl. Radiat. Isotopes 42: 771-773.
- Tajuddin, A. A., Che Wan Sudin, C. W. A. and Bradley, D. A., 1996. Radiographic and scattering investigation on the suitability of *Rhizophora* spp. as tissue equivalent medium for dosimetric study. Radiat. Phys. Chem. 47: 739-740.
- Banjade, D. P., Tajuddin, A. A., and Shukri, A., 2000. A study of *Rhizophora* spp. wood phantom for dosimetric purposes using high-energy photon and electron beams, Appl. Radiat. Iso., 55: 297-302.
- Shakhereet, B. Z., Bauk, S., Tajuddin, A. A., and Shukri, A. ,2009. Mass attenuation coefficient on natural *Rhizophora* spp. woods for X-rays in the 15.77 to 25.27 keV range Radiat. Prot. Dosim. 135: 4-53.
- Marashdeh, M. W., Hashim, R., Tajuddin, A. A., Bauk, S., and Sulaiman, O., 2011. Effect of particle size on the characterization of binderless particleboard made from *Rhizophora* spp. Mangrove wood for use as phantom material Bioresource Technol. 6: 4028-4044.
- Ngu, K. T., Bauk, S., Hashim, R., Tajuddin, A. A., and Shukri, A., 2015. Fabrication of formaldehyde-based particleboards and their mass attenuation coefficients at 15.77, 17.48, 21.18 and 25.27 keV photon energies. Journal of Physical Sciences, 26 (1): 27-33.
- Surani, B. T., 2008. The Suitability of PF, UF and PRF Resins in Term of Structure and Attenuation Properties to be Used in *Rhizophora* spp. Particleboard Phantom. M.Sc. Thesis, Universiti Sains Malaysia.

9. Ababneh, B., Tajuddin, A. A., Hashim, R., and Shuaib, I. L., 2016. Investigation of mass attenuation coefficient of almond gum bonded Rhizophora spp. particleboard as equivalent human tissue using XRF technique in the 16.6-25.23 keV photon energy. *Australas. Phys. Eng. Sci.*, 39 (4): 871-876.
10. Abu Arra, A., Hashim, R., Bau,k S., Kandaiya, S., and Tousi. E.T., 2014. Fabrication and characterization of gum Arabic bonded Rhizophora spp. particleboards, *Mater. Des.*, 60: 108-115.
11. Tousi, E. T., Bauk, S., Hashim, R., Jaafar, M. S, Abuarra, A., 2014. Measurement of mass attenuation coefficients of Eremurus-Rhizophora spp. particleboards for X-ray in the 16.63-25.30 keV energy range. *Radiat. Phys. and Chem.* 103: 119-125.
12. Pizzi, A. and Scharfetter, H., 1989. Adhesives and techniques open new possibilities for the wood processing industry. Part1: Experience with tannin based adhesives. *Eur. J. Wood Wood Prod.*, 39: 85-89.
13. Pizzi, A. and Merlin, M., 1981. A new class of tannins adhesives for exterior particleboard. *Int. J. Adhes. Adhes.* 1(5): 261-264.
14. Safian, A., 2012. Tannin-based Rhizophora spp. Particleboard Breast Phantom at Mammographic Energy. M.Sc. Thesis, Universiti Sains Malaysia.
15. AAPM-21, 1983. Protocol for the determination of absorbed dose from high energy photon and electron beams; Task Group 21 Med. Phys., 10: 741-771.
16. Duvauchelle, P., Peix, G., and Babot, D., 1999. Effective atomic number in the Rayleigh to Compton scattering ratio. *Nucl. Instrum. Methods Section B: Beam Interactions with Materials and Atoms*, 155: 221-228.
17. Brown, S., Bailey, D. L., Willowson, K., and Baldock, C., 2008. Investigation of the linear relationship between linear attenuation coefficients and CT Hounsfield units using radionuclides for SPECT, *Appl. Radiat. Isotopes*, 66: 1206-1212.
18. Berger, M. J. and Hubbell, J. H., 1987. XCOM: Photon cross-sections on a personal computer. *NBSIR* 87-3597.
19. Marashdeh, M. W., Bauk, S., Tajuddin, A. A., and Hashim, R., 2012. Measurement of mass attenuation coefficients of Rhizophora spp. binderless particleboards in the 16.59-25.26 keV photon energy range and their density profile using x-ray computed tomography, *Appl. Radiat. Isotopes*, 70: 656-662.
20. Chang, L., Ho, S. Y., Lee, T. F., Yeh, S. A., Ding, H. J. and Chen, P. Y., 2015. The suitable dose range for the calibration of EBT2 film by the PDD method with a comparison of two curve fitting algorithms. *Physics Research A*, 777: 85-90.
21. Kurudirek, M., 2014. Effective atomic numbers and electron densities of some human tissues and dosimetric materials for mean energies of various radiation sources relevant to radiotherapy and medical applications *Radiation Phys. Chem.*, 102: 139-146

Persian Abstract

DOI: 10.5829/ijee.2017.08.04.05

چکیده

مواد فانتوم ابزار مهمی برای کنترل کیفیت و کارکرد دوزیمتری در فیزیک پزشکی است. Rhizophora spp. تانن پیوند خورده تخته خرده چوب در فانتوم ساخته شد و خواص دزیمتری در فوتون های انرژی بالا و الکترون ها مورد بررسی قرار گرفت. تخته خرده چوب در ابعاد $30 \times 30 \times 1$ سانتی متر و تراکم هدف 1.0 g/cm^3 بر اساس فانتوم آب معمولی استفاده شده در پرتودرمانی ساخته شد. تعداد اتمی موثر تخته خرده چوب بر اساس ترکیبات عنصری اندازه گیری شده با استفاده از تحلیل انرژی اشعه ایکس (EDXA) اندازه گیری شد. ضرایب انقباض جرمی در فوتون با انرژی بالا در فوتون های $16.59 - 25.26$ کیلووات و انرژی های $60 - 137$ Cs اندازه گیری شد. درصد درصد عمق و پارامترهای پرتو تخته خرده چوب در فوتون های ۶ مگاوات و الکترون های ۶ مگاوات با استفاده از نرم افزار Gffchromic EBT2 و سیستم برنامه ریزی درمان (TPS) اندازه گیری شد. نتایج نشان داد که تعداد اتم موثر و چگالی الکترونی تخته خرده چوب به مقدار آب بستگی دارد. ضرایب تضعیف جرمی در فوتون های انرژی بالا نزدیک به مقدار XCOM آب بود. درصد درصد عمق در فوتون های با انرژی بالا و الکترون ها در مقدار ۱۰ درصد در تمام عمق های اندازه گیری شده با مقدار فانتوم آب و آب جامد موافق است. نتایج کلی نشان داد که مناسب بودن ریزوفورا با تانن پیوند خرده است.
